



**NOTES**

1. CONCRETE SHALL CONFORM TO OPSS MUNI 353 AND 1350 SPECIFICATIONS (32MPa, 5.0% TO 8.0% AIR).
2. FIRST STAGE CURB TO BE A CONTINUOUS POUR. SECOND STAGE CONTRACTION JOINTS TO BE SAWCUT EVERY 3.0m (MAXIMUM) AND TO BE 25% OF TOTAL DEPTH.
3. CURING: STAGE 1 & STAGE 2 - CURING COMPOUND - TO BE APPLIED WITHIN HALF HOUR OF FINISHING ON ALL EXPOSED SURFACES.
4. STAGE 1 TO BE THOROUGHLY CLEANED AND WET PRIOR TO STAGE 2 INSTALLATION.
5. ALL REINFORCING TO HAVE 50mm COVER.
6. REINFORCING BAR IN BASE IS 15M ON STRAIGHT AND 10M ON CURVES.
7. BASE ASPHALT TO TO BE SAWCUT SUFFICIENTLY TO ALLOW FOR MECHANICAL COMPACTION OF HL3 FILLER.
8. EXCESS CONCRETE TO BE REMOVED IMMEDIATELY AT TIME OF POURING.
9. IF CONCRETE IS INITIALLY CURED WITH OTHER METHODS DUE TO THE WEATHER CONDITIONS, CURING COMPOUND SHALL BE APPLIED WITHIN 24 HOURS OF FINISHING ON ALL EXPOSED SURFACES.
10. COLD WEATHER PROTECTION SHALL BE USED WHEN DAY TIME TEMPERATURES ARE EXPECTED TO BE BELOW 5° CELSIUS DURING THE CURING COMPOUND PERIOD AS NOTED IN OPSS MUNI 904.

ALL DIMENSIONS ARE IN MILLIMETRES UNLESS OTHERWISE NOTED



**STANDARD TWO STAGE  
CURB & GUTTER**

REVISION NO.: 1  
REVISION DATE: DECEMBER 2025

**C-304**